

RETEXVAL, S.L.

Recubrimientos Textiles Valencia, s.l.

CARACTERISTICAS TECNICAS

ARTICULO / ARTICLE : **CORDURA 1000 PU + WR**

COMPOSICION / COMPOSITION :	TEJIDO BASE : BASE FABRIC	100,00 %	POLIAMIDA 66 TEXTURIZADO
	RECUBRIMIENTO : BACKING	RESINA POLIURETANO + WR	

PESO / WEIGHT :	350,00 GR.M2 +- 5 %	ANCHO / WIDTH :	150 CMS.
-----------------	---------------------	-----------------	----------

NUMERO DE HILOS / NUMBER OF THREADS /CM :	URDIMBRE : 13 +-1 PA. 560 DTEX WARP
	TRAMA : 11 +-2 PA. 560 DTEX WEFT

RESISTENCIA AL DESGARRO / RIPPING STRENGTH : (UNI 4818 : 1.992 P.TE.9)	URDIMBRE : 250 +- 5 % N WARP
	TRAMA : 200 +- 5 % N WEFT

RESISTENCIA A LA TRACCION / BREAKING STRENGTH : (UNI 13934-1 : 2.000)	URDIMBRE : 3.000 +- 5 % N WARP
	TRAMA : 2.400 +- 5 % N WEF

COLUMNA DE AGUA / WATER PRESSURE : (UNI EN 20811 : 1993)	130 CM
---	--------
