

RETEXVAL, S.L.

Recubrimientos Textiles Valencia, s.l.

CARACTERISTICAS TECNICAS

ARTICULO / ARTICLE : **LOIRA 2PU + WR**

COMPOSICION / COMPOSITION :	TEJIDO BASE : BASE FABRIC	00,00% POLIAMIDA
	RECUBRIMIENTO : BACKING	PU + WR

PESO / WEIGHT :	120,00 GR.M2 +- 5 %	ANCHO / WIDTH :	148/150 CMS.
-----------------	---------------------	-----------------	--------------

NUMERO DE HILOS / NUMBER OF THREADS /CM :	URDIMBRE : 44 +-2 PA. 70 WARP
	TRAMA : 29 +-2 PA. 70 WEFT

RESISTENCIA AL DESGARRO / RIPPING STRENGTH : (UNI 4818 : 1.992 P.TE.9)	URDIMBRE : 180 +- 5 % N WARP
	TRAMA : 130 +- 5 % N WEFT

RESISTENCIA A LA TRACCION / BREAKING STRENGTH : (UNI 13934-1 : 2.000)	URDIMBRE : 650 +- 5 % N WARP
	TRAMA : 550 +- 5 % N WEF

HIDROFUGO / HYDROPHOPIC : (UNI EN 20811 : 1993)	98 CMS.
--	---------
