

RETEXVAL, S.L.

Recubrimientos Textiles Valencia, s.l.

CARACTERISTICAS TECNICAS

ARTICULO / ARTICLE :

LOIRA PVC

COMPOSICION / COMPOSITION :	TEJIDO BASE : BASE FABRIC	18,50% POLIAMIDA
	RECUBRIMIENTO : BACKING	81,50 % PVC

PESO / WEIGHT : **310,00 GR.M2** +- 5 %

ANCHO / WIDTH : **148/150 CMS.**

NUMERO DE HILOS / NUMBER OF THREADS /CM :	URDIMBRE : 44 +-2 PA. 70 WARP
	TRAMA : 29 +-2 PA. 70 WEFT

RESISTENCIA AL DESGARRO / RIPPING STRENGTH : (UNI 4818 : 1.992 P.TE.9)	URDIMBRE : 100 +- 5 % N WARP
	TRAMA : 90 +- 5 % N WEFT

RESISTENCIA A LA TRACCION / BREAKING STRENGTH : (UNI 13934-1 : 2.000)	URDIMBRE : 750 +- 5 % N WARP
	TRAMA : 590 +- 5 % N WEF

HIDROFUGO / HYDROPHOPIC : **NO**
