

RETEXVAL, S.L.

Recubrimientos Textiles Valencia, s.l.

CARACTERISTICAS TECNICAS

ARTICULO / ARTICLE : MILAN RESINADO

COMPOSICION / COMPOSITION :	TEJIDO BASE : BASE FABRIC	85,00% POLIESTER
	RECUBRIMIENTO : BACKING	15,00 %PVC

PESO / WEIGHT :	150,00 GR.M2 +- 5 %	ANCHO / WIDTH :	160 CMS.
-----------------	---------------------	-----------------	----------

NUMERO DE HILOS / NUMBER OF THREADS /CM :	URDIMBRE : 22 +-2 PES. 300 DTEX. WARP
	TRAMA : 18 +-2 PES. 300 DTEX. WEFT

RESISTENCIA AL DESGARRO / RIPPING STRENGTH : (UNI 4818 : 1.992 P.TE.9)	URDIMBRE : 120 +- 5 % N WARP
	TRAMA : 115 +- 5 % N WEFT

RESISTENCIA A LA TRACCION / BREAKING STRENGTH : (UNI 13934-1 : 2.000)	URDIMBRE : 1.000 +- 5 % N WARP
	TRAMA : 800 +- 5 % N WEF

COLUMNA DE AGUA / WATER PRESSURE : (UNI)	1000
---	------