

RETEXVAL, S.L.

Recubrimientos Textiles Valencia, s.l.

CARACTERISTICAS TECNICAS

ARTICULO / ARTICLE :

SENA PVC

COMPOSICION / COMPOSITION :	TEJIDO BASE : BASE FABRIC	29,90% POLIAMIDA
	RECUBRIMIENTO : BACKING	70,10 %PVC

PESO / WEIGHT : 350,00 GR.M2 +- 5 %

ANCHO / WIDTH : 160 CMS.

NUMERO DE HILOS / NUMBER OF THREADS /CM :	URDIMBRE : 20 +-2 PA. 210 WARP
	TRAMA : 20 +-2 PA. 210 WEFT

RESISTENCIA AL DESGARRO / RIPPING STRENGTH : (UNI 4818 : 1.992 P.TE.9)	URDIMBRE : 110 +- 5 % N WARP
	TRAMA : 120 +- 5 % N WEFT

RESISTENCIA A LA TRACCION / BREAKING STRENGTH : (UNI 13934-1 : 2.000)	URDIMBRE : 970 +- 5 % N WARP
	TRAMA : 750 +- 5 % N WEF

COLUMNA DE AGUA / WATER PRESSURE : (UNI)	1000
---	------
